CLAIMS

1. A vinyl chloride resin composition comprising 100 parts by mass of a vinyl chloride resin and a co-ground mixture of (a) 0.001 to 10 parts by mass of at least one member selected from the group consisting of an organic phosphoric ester compound and a metal salt thereof and (b) 0.001 to 10 parts by mass of a grinding aid.

2. The vinyl chloride resin composition according to claim 1, wherein the organic phosphoric ester compound and its metal salt are represented by general formula (I):



(I)

wherein $R_1$, $R_2$, and $R_3$ each represent a hydrogen atom or a straight-chain or branched alkyl group having 1 to 18 carbon atoms; $R_4$ represents a hydrogen atom or a methyl group; n represents 1 or 2; M represents a hydrogen atom or an alkali metal atom when n is 1, or M represents an alkaline earth metal atom or a zinc atom when n is 2.

3. The vinyl chloride resin composition according to claim 2, wherein M is an alkali metal atom or a zinc atom.

4. The vinyl chloride resin composition according to claim 2 or 3, wherein $R_1$ and $R_2$ are each a tert-butyl group, and $R_3$ and $R_4$ are each a hydrogen atom.

5. The vinyl chloride resin composition according to any one of claims 1 to 4, wherein the grinding aid is at least one member selected from the group consisting of an aliphatic organic acid metal salt, hydrotalcite, a powdered silica, and a vinyl chloride resin.

6. The vinyl chloride resin composition according to claim 5, wherein the aliphatic organic acid metal salt is a lithium salt, calcium salt, magnesium salt or zinc salt of stearic acid.

7. The vinyl chloride resin composition according to any one of claims 1 to 6, wherein the co-ground mixture has an average particle size of 0.1 to 100 μm.